

145 Lehigh Avenue, Lakewood, NJ 08701 **T:** 732.634.5700 **F:** 732.634.1430 alphainc.com

ALPHA - MARITEX STYLE 8459-2-SS

DESCRIPTION

Alpha Maritex Style 8459-2-SS is a fiberglass fabric impregnated with a specially formulated silicone rubber designed to meet the rigid requirements for use in nuclear reactors. This product is designed specifically for high temperature (500 ° F) removable pads, flange and valve covers. This product can be manufactured to meet the requirements of NRC 1.36 as well as MIL-I-24244. This (Heavy Duty) silicone impregnated fiberglass fabric is used where more wear resistance is needed.

ADVANTAGES

Aluminum color, Water and Oil resistant, Acid and Alkali resistant, Flame retardant, Low Smoke, Easily sewn, Adhesive bonded or sealed. The special high temperature, flame retardant silicone rubber provides greater life and improved resistance to abrasion, flexing, tear and puncture.

APPLICATIONS

Removable Insulation Pad Covering, Flange and Valve covers, Welding Curtains and Splash Shields, Safety Clothing, Equipment Covers, Flexible Connectors (Expansion Joints).

PROPERTY DATA STYLE 8459-2-SS

METHOD	<u>VALUES</u> *		
	<u>ENGLISH</u>		<u>METRIC</u>
ASTM-D-3776	34.0 oz/sy ± 10%		$1156 \text{ g/m}^2 \pm 10\%$
ASTM-D-1777	0.037" ± 10%		0.940 mm ± 10%
TENSILE STRENGTH ASTM-D-5034	Warp-	400 lbs/inch min.	71.44 kg/cm
	Fill-	350 lbs/inch min.	62.51 kg/cm
TEAR STRENGTH ASTM-D-5587	Warp-	65 lbs min.	29.48 kg
	Fill-	55 lbs min.	24.95 kg
ASTM-D-3786	750 psi min.		52.5 kg/cm ²
FLAME RESISTANCE ASTM D-6413	Char Length	1 inch max.	2.54 cm max.
	Afterglow	1 second max.	1 second max.
	Flame Out	1 second max.	1 second max.
NCE	-67 °F to +500	°F	-55 °C to 260 °C
BASE FABRIC and WEAVE Fiberglass/Satin Weave			
COLOR and COATING Silver			
ASS BASE FABRIC 1,200 °F Melt Point		649 °C Melt Point	
	ASTM-D-3776 ASTM-D-1777 ASTM-D-5034 ASTM-D-5587 ASTM-D-3786 ASTM D-6413	ASTM-D-3776 ASTM-D-1777 ASTM-D-5034 ASTM-D-5034 Warp-Fill- ASTM-D-5587 Warp-Fill- ASTM-D-3786 ASTM D-6413 Char Length Afterglow Flame Out -67 °F to +500 Fiberglass/Sati	## ASTM-D-3776 34.0 oz/sy ± 10% ASTM-D-1777 0.037" ± 10% ASTM-D-5034 Warp- 400 lbs/inch min. Fill- 350 lbs/inch min. ASTM-D-5587 Warp- 65 lbs min. Fill- 55 lbs min. ASTM-D-3786 750 psi min. ASTM D-6413 Char Length 1 inch max. Afterglow 1 second max. Flame Out 1 second max. Flame Out 1 second max. Flame Out 500 °F Fiberglass/Satin Weave Silver Silicone

DATA SHEET: 13431 REV: H DATE: 08/03/12 *All values are nominal unless otherwise

Specializing in marine, aerospace, automotive and commercial fabrics for thermal and industrial applications

All statements herein are expressions of opinion that we believe to be accurate and reliable, but are presented without guaranty or responsibility on our part. Statements concerning possible use of our products are not intended as recommendations for their use alone or in combination with any materials or elements to infringe any patents. No patent warranty of any kind, express or implied, is made or intended.



DATA SHEET: 13431 REV: H DATE: 08/03/12 *All values are nominal unless otherwise

Specializing in marine, aerospace, automotive and commercial fabrics for thermal and industrial applications

All statements herein are expressions of opinion that we believe to be accurate and reliable, but are presented without guaranty or responsibility on our part. Statements concerning possible use of our products are not intended as recommendations for their use alone or in combination with any materials or elements to infringe any patents. No patent warranty of any kind, express or implied, is made or intended.