

145 Lehigh Avenue, Lakewood, NJ 08/01 **T:** 732.634.5700 **F:** 732.634.1430 alphainc.com

ALPHA - MARITEX STYLE 4011

DESCRIPTION

Alpha Maritex Style 4011 is a four-ply lamination of alternating layers of fiberglass fabric.

APPLICATIONS

Alpha Maritex Style 4011 has been specifically designed as a barrier material to prevent absorption of flammable materials into the insulation filler in removable blankets. Some of the many uses for this product include the following: welding curtains, insulation facings, radiation shields and blanket material.

ADVANTAGES

Alpha Maritex Style 4011 provides an excellent vapor barrier, as well as being a fire stop. The product also provides the user with an excellent barrier to hydrocarbons.

PROPERTY DATA				
STYLE 4011				
CHARACTERISTIC	METHOD	<u>VALUES</u> *		
		<u>ENGLISH</u>		<u>METRIC</u>
WEIGHT	ASTM-D-3776	22 oz/sy ± 10%		$748 \text{ g/m}^2 \pm 10\%$
THICKNESS	ASTM-D-1777	0.036" ± .004"		0.914 mm ± .102 mm
TENSILE STRENGTH	ASTM-D-5035	Warp-	250 lbs./inch	44.65 kg/cm
		Fill-	175 lbs/inch	31.26 kg/cm
TEAR STRENGTH	ASTM-D-5587	Warp-	50 lbs.	22.68 kg
		Fill-	50 lbs.	22.68 kg
BURST STRENGTH	ASTM-D-3786	450 psi		31.5 kg/cm ²
FLAME RESISTANCE	ASTM D-6413	Char Length	1 inch max.	2.54 cm max.
		Afterglow	1 sec. max.	1 sec. max.
		Flame Out	1 sec. max.	1 sec. max.
TEMPERATURE RESISTANCE		Service Temperature = 500 °F		260 °C
BASE FABRIC and WEAVE		Fiberglass/Plain Weave		
COLOR and COATING		Fabric Color/Aluminum Foil		

DATA SHEET: 13110 REV: C DATE: 03/06/12 *All values are nominal unless otherwise specified.

Specializing in marine, aerospace, automotive and commercial fabrics for thermal and industrial applications

All statements herein are expressions of opinion that we believe to be accurate and reliable, but are presented without guaranty or responsibility on our part. Statements concerning possible use of our products are not intended as recommendations for their use alone or in combination with any materials or elements to infringe any patents. No patent warranty of any kind, express or implied, is made or intended.