



Midwest Fasteners
450 Richard St.
Miamisburg, OH 45342
Website: www.midwestfasteners.com

Toll Free: (800) 852-8352
Phone: (937) 866-0463
Fax: (937) 866-4174
Email: sales@midwestfasteners.com

[All Categories](#) > [Insulation Fasteners](#) > [Hanger Adhesives](#) > **IHA-177 Insulation Hanger Adhesive**

IHA-177 INSULATION HANGER ADHESIVE

Product Data:

MIDWEST Fasteners HANGER ADHESIVE is a high strength, heavy-bodied adhesive, specifically formulated for adhering anchors for hanging insulation.

IHA-177 HANGER ADHESIVE bonds metal and nylon anchors to metal, concrete or masonry surfaces. The product can also be used to install metal or ceramic wall fixtures and in tile applications.

MIDWEST Fasteners HANGER ADHESIVE is also available for use as a general-purpose construction adhesive in applications requiring a high strength bond, or in applications subjected to high temperatures.

Special Characteristics:

- Excellent thermal shock resistance
- High bond strength
- Water resistant
- Immediate grab
- Mildew resistant
- Non-slip formula

Directions for Use:

1. Use only after careful consideration of the warnings, directions, and first aid instructions given.

2. Surface Preparation: Surfaces to be bonded should be clean, dry and free of any dust, frost, wax, moisture, dirt, grease, oil, rust, or other contaminants. Do not use over painted surfaces. Many protective coatings are not compatible with Anchor Adhesive.

3. Adhesive Preparation: Adhesive should be stored at room temperature (60°F to 80°F) for at least 24 hours prior to use.

4. Working Temperature: For best results, adhesive and materials to be bonded should be 30°F to 120°F.

5. Adhesive Application: Do not apply at temperatures below 30°F. Prepare and install one anchor at a time. Apply a dab (the size of a small walnut) of adhesive to the anchor base with a putty knife and immediately (maximum open time is 10 minutes) press anchor firmly into place, with a slight twisting motion. For proper adhesion, insure that the film of adhesive covering the anchor base (after the anchor has been firmly pressed into place) is protruding

6. Installing Anchor Adhesive to Concrete Surfaces: New concrete surfaces need to cure a minimum of 28 days in order to ensure best adhesion. All concrete surfaces should be high pressure water blasted or sand blasted to remove any surface curing agents

Adhesive



and all foreign matter. Spread anchor adhesive on anchor base allowing solvent to flash off for several minutes before pressing anchor firmly into place with a slight twisting motion. Do not apply load until application is completely dry.

PACKAGING INFORMATION

Size	Packed	Part #	Weight
GALLON	4/carton	IHA-177-GA	39 lbs. /carton

*MIDWEST Fasteners does not ship IHA-177 Adhesive by Air; standard shipments are UPS or Motor Freight. Also sold by MIDWEST only in carton-lot quantities.

Please click the Request Information button to configure your IHA-177 Insulation Hanger Adhesive.

[less](#)

[Order](#) | [Specifications](#) | [Configure Parts](#)

Order

Specifications

Base	Thermoplastic Rubber
Type	Solvent
Solids Content	64 %
Color	Light Brown
Weight	9 lb/gal
Shear Strength	Greater than 600 psi (AFG 01)
Water Resistance	Excellent
Consistency	Gun Grade Mastic
Application Temperature	30 to 120 °F
Extrudability	Excellent (ASTM C 731)
Service Temperature	-30 to 250 °F
Shelf Life	12 months
Storage Temperature	Store at room temperature with cross ventilation.
Clean-up	Mineral Spirits, exercising safe practices OSHA Class 1B liquid. Store per 29 CFR 1910, 106.
Coverage	500-1000 anchors per gallon
Flammability	Flammable, Red Label
Flash Point	(ASTM D 3828) -9 °F

Open Time

15 minutes at 75°F and 50% relative humidity

Configure Parts