

SeaRox® S 337 Alu tape

Alutape to seal joints of insulation. Low flame spread approval.



Product properties

		Norm
Thickness	0.06 mm +- 0.02	AFERA 4006
Adhesion to steel	4.0 N/cm ²	AFERA 4001
Tensile strenght	12 N/cm ²	AFERA 4004
Elongation at break	5%	AFERA 4004
Approvals	IMO A.653 (16) UL 723 BS 476 Part 6 British building regulation SISIR ISO 9001	
Operating temperatures	- 20° C to + 110° C	
Storage	The rolls of tape must be stored flat on their cut edges in the original packing until required for use, and must be protected from dust, heat, moisture, direct sunlight, corrosion and solvent fumes at a recommended temperature of 10°C to 25°C. It is recommended that the tape be used within 12 months after receipt of the material.	
Length	50 m per roll	
Width	50, 75 mm	

As ROCKWOOL has no control over insulation design and workmanship, accessory materials or applications conditions, ROCKWOOL does not warranty the performance or result of any installation containing ROCKWOOL products. ROCKWOOL's overall liability and the remedies available are limited by the general terms and conditions of sale. This warranty in lieu of all other warranties and conditions expressed or implied, including the warranties of merchantability and fitness for a particular purpose. ROCKWOOL Technical Insulation reserves the right to make necessary product changes at any time. Technical specifications are thus stated subject to change.

ROCKWOOL® Technical Insulation, ROCKWOOL®, SeaRox® and ProRox® are registered trademarks of ROCKWOOL International A/S and cannot be used without a prior written consent.