

# SeaRox® SL 340 ALU

SeaRox SL 340 ALU is a semi-rigid slab of stone wool. Excellent properties for easy handling and installation. The product is as standard supplied with reinforced alu foil.



## Application

SeaRox SL 340 ALU is primarily used for sound insulation. Perfect in combination as comfort and high noise reduction.

## Product properties

Properties	Performance		Norm
Thermal conductivity	T (°C) λ (W/mK)	10 0,034	EN 12667
Nominal density	80 kg/m <sup>3</sup>		EN 1602 / IMO
Compressive strength	-		EN 826
Fire classification	Non-combustible Low flame-Spread Properties		Acc. IMO FTP code
Water absorption (short term)	< 1 kg/m <sup>2</sup>		EN 1609
Max. Application Temperature	Wool 250°C, ALU facing 80°C		-
Sound absorption directly mounted	-		ISO 354 (approximated) Evaluated after ISO 11 654
Facings	Reinforced alu foil		IMO A.653(16) (low flame - spread)

## Dimensions

### SeaRox SL 340 ALU

Thickness (mm): 50 mm Length (mm): 1000 mm Width (mm): 600 mm

Local variations in standard dimensions might occur.



0575

As ROCKWOOL has no control over insulation design and workmanship, accessory materials or applications conditions, ROCKWOOL does not warranty the performance or result of any installation containing ROCKWOOL products. ROCKWOOL's overall liability and the remedies available are limited by the general terms and conditions of sale. This warranty in lieu of all other warranties and conditions expressed or implied, including the warranties of merchantability and fitness for a particular purpose. ROCKWOOL Technical Insulation reserves the right to make necessary product changes at any time. Technical specifications are thus stated subject to change.

ROCKWOOL® Technical Insulation, ROCKWOOL®, SeaRox® and ProRox® are registered trademarks of ROCKWOOL International A/S and cannot be used without a prior written consent.