



## DOWSIL™ 736 Heat Resistant Sealant

Non-slumping sealant designed for sealing and bonding applications exposed to temperatures as high as 315°C (600°F)

### Features & Benefits

- Will not sag or run
- May be applied overhead or on side walls
- May be used in applications with continuous exposure to 260°C (500°F) and intermittent exposure to 315°C (600°F)

### Composition

- One-part silicone

### Applications

The high temperature properties of this sealant make it ideally suited for:

- Sealing and encapsulating heating elements in appliances
- Aerospace gasketing
- Moving oven belts
- Industrial ovens
- Bag filters on smoke stacks
- Other critical bonding, sealing, potting, encapsulating and protective coatings where parts must perform at high temperatures

### Typical Properties

Specification Writers: These values are not intended for use in preparing specifications.

Property	Unit	Result
<b>As Supplied</b>		
Color		Red
Flow/Slump		Nil
Extrusion Rate (1/8 Inch Orifice, 90 psi)	g/min	390
Specific Gravity		1.04
<b>Cure Characteristics – Exposed to Air, 25°C (77°F) and 50 Percent RH</b>		
Skin-over Time	minutes	10
Tack-free Time	minutes	17
Cure Time (3 mm [1/8 Inch] Thickness)	hours	24

## Typical Properties (Cont.)

Property	Unit	Result
<b>As Cured - After 72 Hours at 25°C (77°F) and 50 Percent RH</b>		
Durometer Hardness, Shore A	points	26
Tensile Strength	psi	350
Elongation	percent	600

### Description

DOWSIL™ 736 Heat Resistant Sealant is a one-part, nonslumping paste that cures to a rubbery solid at room temperature on exposure to water vapor in the air. This silicone product is formulated to perform at temperatures ranging from -65 to 260°C (-85 to 500°F) for continuous operation and to 315°C (600°F) for intermittent exposure. It can be used for numerous sealing and bonding applications.

### Listings/ Specifications

- Complies with FDA Regulation 21 CFR 177.2600, subject to end-use compliance with any applicable total extractives limitations, and for incidental food contact use in official establishments operating under the Federal Meat and Poultry Products Inspection Program
- Listed by the National Sanitation Foundation under Standard 51 for direct contact with food
- Listed by Underwriters Laboratories
- Designed to meet the requirements of MIL-A-46106 Rev. B

### How to Use

#### Application

DOWSIL™ 736 Heat Resistant Sealant is supplied ready to use. Under pressure, it flows readily from its container. The paste-like consistency makes it easy to work; a spatula or wooden paddle can be used for tooling the surface.

#### Tack-free Time

The cure progresses inward from the surface when exposed to humidified air. At 77°F (25°C) and 50 percent relative humidity, the sealant forms a tack-free skin within 17 minutes. Tooling is not practical after the skin begins forming and should be completed within five minutes after application even though this may require alternate periods of applying and tooling. If masking tape is used to mark off an area, it should be removed immediately after tooling.

#### Cure Time

Cure time is affected by relative humidity, degree of confinement and cross-sectional thickness of the sealant. Sections up to 3 mm [1/8 inch] thick become rubbery solids in about 24 hours at 25°C (77°F) and 50 percent relative humidity. Less moisture content reduces the time required slightly. In 24 hours, sections up to 3 mm [1/8 inch] thick cure to a rubber.

## How to Use (Cont.)

### Confined Cure

In applications where DOWSIL™ 736 Heat Resistant Sealant may be partially or totally confined during cure, the time required for proper cure is generally lengthened by the degree of confinement. It is possible, with absolute confinement, that cure will not be completed. Metal-to-metal bonds should not overlap more than one inch. Every application involving confinement during cure should be thoroughly tested before use. Curing time increases with the thickness of the sealant.

Note: The odor given off during cure is due to the liberation of acetic acid. This odor disappears as the cure progresses and is not detectable after the cure is complete.

### Bonding

1. Thoroughly clean and degrease metal and plastic surfaces using DOWSIL™ OS (Ozone Safe) fluids or another suitable solvent. Rubber surfaces should be roughened with sandpaper, then wiped with DOWSIL™ OS fluids or another suitable solvent. Follow all precautions given on the solvent container label.
2. For stronger, more uniform bonds, apply a thin film of DOWSIL™ 1200 Prime Coat or DOWSIL™ P5200 Adhesion Promoter to all surfaces except rubber and silicone rubber. Allow to air-dry for 30 to 45 minutes at room temperature. (Full instructions are provided with the prime coat.)

Note: DOWSIL™ 1200 Prime Coat or DOWSIL™ P5200 Adhesion Promoter are flammable and are not suitable for use in food contact applications. Keep away from heat, sparks and open flames. Use only with adequate ventilation.

3. Apply DOWSIL™ 736 Heat Resistant Sealant to the prepared surface in a uniform thickness. In those cases where the sealant is to be used between two surfaces, put the second surface in place, using enough pressure to displace the air but not the sealant.
4. Let the unit stand undisturbed at room temperature until cured.

### Sealing

Using DOWSIL™ 736 Heat Resistant Sealant in sealing applications follows approximately the same step-by-step procedures as outlined for bonding applications. After preparing the surfaces and priming where required, the sealant is applied by forcing it into the joint or seam to obtain full contact between the sealant and the surface.

## Handling Precautions

PRODUCT SAFETY INFORMATION REQUIRED FOR SAFE USE IS NOT INCLUDED IN THIS DOCUMENT. BEFORE HANDLING, READ PRODUCT AND SAFETY DATA SHEETS AND CONTAINER LABELS FOR SAFE USE, PHYSICAL AND HEALTH HAZARD INFORMATION. THE SAFETY DATA SHEET IS AVAILABLE ON THE DOW WEBSITE AT DOW.COM, OR FROM YOUR DOW SALES APPLICATION ENGINEER, OR DISTRIBUTOR, OR BY CALLING DOW CUSTOMER SERVICE.

## Usable Life and Storage

Product should be stored at or below 32°C (90°F) in original, unopened containers.

## Limitations

DOWSIL™ 736 Heat Resistant Sealant is not recommended:

- For continuous underwater immersion where adhesion or structural bonding is required
- On concrete, brick, mortar or other masonry surfaces
- On surfaces to be painted; paints do not adhere well to sealant (paint before applying sealant)
- On materials such as impregnated woods or oil-based caulks that bleed oils
- In totally confined areas; atmospheric moisture is required for cure
- On Teflon coated materials, polyethylene, polypropylene or methylmethacrylate (Plexiglas); sealant will not adhere well
- On or near sensitive metals such as copper, brass, zinc, carbon steel, galvanized iron or magnesium; these metals may be corroded, especially in confined cure conditions, due to the acetic acid released during the cure
- On some plastics; may cause stress cracks; test before use

This product is neither tested nor represented as suitable for medical or pharmaceutical uses.

## Health and Environmental Information

To support customers in their product safety needs, Dow has an extensive Product Stewardship organization and a team of product safety and regulatory compliance specialists available in each area.

For further information, please see our website, [dow.com](http://dow.com) or consult your local Dow representative.

## Disposal Considerations

Dispose in accordance with all local, state (provincial) and federal regulations. Empty containers may contain hazardous residues. This material and its container must be disposed in a safe and legal manner.

It is the user's responsibility to verify that treatment and disposal procedures comply with local, state (provincial) and federal regulations. Contact your Dow Technical Representative for more information.

## Product Stewardship

Dow has a fundamental concern for all who make, distribute, and use its products, and for the environment in which we live. This concern is the basis for our product stewardship philosophy by which we assess the safety, health, and environmental information on our products and then take appropriate steps to protect employee and public health and our environment. The success of our product stewardship program rests with each and every individual involved with Dow products - from the initial concept and research, to manufacture, use, sale, disposal, and recycle of each product.

## Customer Notice

Dow strongly encourages its customers to review both their manufacturing processes and their applications of Dow products from the standpoint of human health and environmental quality to ensure that Dow products are not used in ways for which they are not intended or tested. Dow personnel are available to answer your questions and to provide reasonable technical support. Dow product literature, including safety data sheets, should be consulted prior to use of Dow products. Current safety data sheets are available from Dow.

dow.com

**NOTICE:** No freedom from infringement of any patent owned by Dow or others is to be inferred. Because use conditions and applicable laws may differ from one location to another and may change with time, Customer is responsible for determining whether products and the information in this document are appropriate for Customer's use and for ensuring that Customer's workplace and disposal practices are in compliance with applicable laws and other government enactments. The product shown in this literature may not be available for sale and/or available in all geographies where Dow is represented. The claims made may not have been approved for use in all countries. Dow assumes no obligation or liability for the information in this document. References to "Dow" or the "Company" mean the Dow legal entity selling the products to Customer unless otherwise expressly noted. NO WARRANTIES ARE GIVEN; ALL IMPLIED WARRANTIES OF MERCHANTABILITY OR FITNESS FOR A PARTICULAR PURPOSE ARE EXPRESSLY EXCLUDED.

