

PRODUCT DATA SHEET

Super Caltemp® Gold 1700

Super Caltemp Gold 1700 block is an inorganic, non-combustible, high-temperature insulation tailored for systems operating up to 1700°F(927°C), and is composed primarily of hydrous calcium silicate. The gold color provides positive identification that it is Asbestos Free. Super Caltemp Gold 1700 meets or exceeds the physical and thermal property requirements of ASTM C533, Type II.

THE ADVANTAGES

- Excellent Resistance to damage, enhancing the life of the system.
- Consistent Thermal Performance to 1700°F.
- Non-combustible.
- Structural Strength protects against damage to lagging.
- No Organic Binders; no loss of insulation integrity.

APPLICATIONS

Applications include, high-temperature insulation for curved vessels and large diameter pipes, boiler walls, high temperature ducts, flues, industrial breeching and as refractory backer in furnaces, boilers and kilns. Super Caltemp Gold 1700 may be double layered in the field for greater thicknesses.

APPLICATION FORMS AND SIZES

Super Caltemp Gold 1700 is manufactured in 12" x 36" (305 mm x 914 mm) sheets, flat or 3-V scored. Thicknesses range from 1" (25 mm) through 3" (76 mm).

STANDARD SIZES	
Thickness	1", 1½", 2", 2½", 3" (25, 38, 51, 64, 76 mm)
Sheet Size	12" x 36" (305 mm x 914 mm)
Dimensional Tolerances: Length and Width Thickness	± 1/8" (3 mm) ± 1/16" (0.8 mm)

LINEAR SHRINKAGE AFTER 24 HRS AT TEMPERATURE

Temperature°F (°C)	Length	Width	Thickness	Weight Loss
1700°F (927°C)	1.0 %	1.0 %	2.1 %	9.6 %

ADDITIONAL INFORMATION AND SDS

Please visit our website at www.jm.com/industrial

**CUSTOMER SERVICE, TECHNICAL & GENERAL
INFORMATION (800) 866-3234**



SUPER CALTEMP® GOLD 1700
OPERATING TEMPERATURE LIMIT: 1700°F (927°C)

SPECIFICATION COMPLIANCES

ASTM C165 Compressive Strength@5% Deformation	>100 psi (>690 kPa)
ASTM C203 Flexural Strength	> 50 psi (>345 kPa)
ASTM C447 Maximum Recommended Continuous Service Temperature	1700°F (927°C)
ASTM C533 Type II Density (Average)	18 pcf (288 kg/m³)
ASTM C533 Material Specification	Type II
ASTM C795/C871/C692 Corrosion: Austenitic Stainless Steel	Passes
ASTM E84 Flame Spread/Smoke Developed	0/0
ASTM E136 Non-Combustible	Passes
Moisture Content, Normal Percentage of Dry Weight	4
MIL-I-2819	Class 3

THERMAL CONDUCTIVITY

Mean Temperature		"k"	
°F	°C	Btu • in/(hr • ft² • °F)	W/m • °K
200	93	0.54	0.078
400	204	0.61	0.088
600	315	0.67	0.097
800	427	0.73	0.105

PRODUCT CERTIFICATION

When ordering material to comply with any government specification or any other listed specification, a statement of that fact must appear on the purchase order. Government regulations and other listed specifications require specific lot testing, and prohibit the certification of compliance after shipment has been made. There may be additional charges associated with specification compliance testing. Please refer to IND-CSP-3 for Certification Procedures and Charges. Call customer service for more information.

ISO 9000 CERTIFICATION

Thermo-12 Gold is designed, manufactured, and tested in our own facilities, which are certified and registered to stringent ISO 9000(ANSI/ASQ 90) series quality standards. This certification, along with regular independent third-party auditing for compliance, is your assurance that this product delivers consistent high quality.