

PRODUCT DATA SHEET

Super Firetemp X

Super Firetemp X is an inorganic, non-combustible, high-temperature insulation for use in industrial equipment and building systems. It can be used on systems operating up to 1700°F (927°C). Composed primarily of lime, silica and reinforcing fibers. This product is white, essentially dust-free, and contains no asbestos, and meets or exceeds ASTM C 656, Type II, Grade 7.

THE ADVANTAGES

- Assured Fire Resistance
- Durable
- Economical

APPLICATIONS

Super Firetemp X has high strength as well as exceptional insulation qualities. It can be readily machined into component parts of many sizes and shapes. Uses include oven and furnace walls, structural supports, against the shell of steel ladles and torpedo cars, behind the refractory brick and ramming castable of trundages to help keep the metal at a higher temperature and protect against thermal spalling of the refractory brick.

AVAILABLE FORMS AND SIZES

Thickness 1/2", 3/4", 1", 1 1/2", 2" (13, 19, 25, 38, 51 mm)
 Sheet Size 4' x 4' (1.22 m x 1.22 m)
 4' x 8' (1.22 m x 2.44 m)

Super Firetemp X is available with a sanded finish on one or both sides. The sanded surfaces are smooth and easy to machine.

DIMENSION TOLERANCES

Length and Width +/- 1/8" (3.2 mm)
 Thickness +/- 1/8" (3.2 mm) Sanded One Side
 +/- 1/16" (1.6 mm) Sanded Two Sides

LINEAR SHRINKAGE AFTER 24 HOURS AT TEMPERATURE, %

Temperature °F (°C)	Length	Width	Thickness	Weight Loss
1700°F (927°C)	0.7%	0.8%	3.3%	9.9%

THERMAL CONDUCTIVITY

Mean Temperature		"k"	
°F	°C	Btu · in/(hr · ft² · °F)	W/m · °K
200	93	0.65	0.094
400	204	0.70	0.101
600	316	0.75	0.108
800	427	0.80	0.115



SUPER FIRETEMP X®
OPERATING TEMPERATURE LIMIT: 1700°F (927°C)

SPECIFICATION COMPLIANCE

ASTM C656	Type II, Grade 7
ASTM C795 Corrosion: Austenitic Stainless Steel	Passes
ASTM E72	Passes
ASTM E84 Surface Burning Characteristics	Flame Spread -0 Smoke Developed -0
ASTM E136 Non-Combustible	Passes
Density (Avg.)	40 pcf (641 kg/m³)
Maximum Recommended Continuous Service Temp.	1700°F (927°C)
Flexural Strength (Avg.)	1000 psi (6895 kPa)
Compressive Strength @10% deformation (Avg.)	2000 psi (13790 kPa)
Screw Holding Strength (lb/screw), #8 Screw 1/2" (13 mm) Penetration 7/8" (22 mm) Penetration	80 lbs. (36.3 kg) 200 lbs. (90.7 kg)
Surface Hardness (Units) (Per Type "D" Durameter)	Top Surface - 80 Bottom Surface - 80
Moisture Content, Normal % of Dry Weight (Avg.)	4%

ADDITIONAL INFORMATION AND SDS

Please visit our website at www.jm.com/industrial

CUSTOMER SERVICE, TECHNICAL & GENERAL INFORMATION (800) 866-3234

CODE COMPLIANCE

Super Firetemp X undergoes stringent tests to comply with some of the toughest fire codes in the US and Canada.



ISO 9000 CERTIFICATION

Super Firetemp X is manufactured under an ISO 9001:2000 registered quality system. This registration, along with regular independent third-party auditing for compliance, is your assurance that all our products deliver consistently high quality.

PRODUCT CERTIFICATION

When ordering material to comply with any government specification or any other listed specification, a statement of that fact must appear on the purchase order. Government regulations and other listed specifications require specific lot testing, and prohibit the certification of compliance after shipment has been made. There may be additional charges associated with specification compliance testing. Please refer to IND-CSP-3 for Certification Procedures and Charges. Call customer service for more information.

CONSOLIDATION UNDER LOAD (in/in)

Pressure		Deflection Under Load	Permanent Consolidation
psi	kPa		
200	1,379	0.008	0.002
500	3,448	0.014	0.002
1000	6,895	0.022	0.003
2000	13,790	0.059	0.005
3000	20,685	0.120	0.057
4000	27,580	0.243	0.164
5000	34,475	0.325	0.248
6000	41,370	0.364	0.287
7000	48,265	0.412	0.337

Industrial Insulation Group, LLC manufactures MinWool-1200® mineral fiber pipe, block and a variety of other insulations; Thermo-12® Gold Calcium Silicate pipe and block insulation; Microporous Blanket Insulation; Super Firetemp® fireproofing board; SprouleWR-1200® Perlite pipe and block insulation; high-temperature adhesives, and insulating finishing cement. The physical and chemical properties presented herein represent typical, average values obtained in accordance with accepted test methods and are subject to normal manufacturing variations. They are supplied as a technical service and are subject to change without notice. Numerical flame spread and smoke developed ratings are not intended to reflect hazards presented by these or any other materials under actual fire conditions. Check with the Customer Service Office to assure current information. All Industrial Insulation Group products are sold subject to the Johns Manville Limited Warranty and Limitation of Remedy. For a copy of the Johns Manville Limited Warranty and Limitation of Remedy, email info.industrial@jm.com.

CUSTOMER SERVICE
TECHNICAL & GENERAL INFORMATION
 (800) 866-3234



2100 LINE STREET • BRUNSWICK, GA 31520