

ProRox® SL 760^{NA}

ProRox® SL 760^{NA} is a semi-rigid mineral wool (stone wool) multi-purpose acoustic insulation board that can be fabricated for use in light weight panel applications.



Product properties in accordance with ASTM C612

Properties	Performance								Norms
Thermal conductivity	T_m (°F)	75	100	200	300				ASTM C177
	λ (BTU.in/hr.ft ² .°F)	0.24	0.26	0.31	0.35				
	T_m (°C)	24	38	93	149				
	λ (W/mK)	0.035	0.037	0.045	0.050				
Maximum Service Temperature	Hot Surface Performance: 1200°F- (650°C) Non-Combustible Linear Shrinkage: < 1 % at 1200°F- (650°C)								ASTM C411 ASTM E136 / CAN4 S114 ASTM C356
Reaction to fire	Surface burning characteristics Flame spread index = 0 ; Smoke development index = 0								ASTM E84 (UL 723) CAN/ULC S102
Density	Actual Density = 3.0 lb/ft ³ - (48 kg/m ³)								ASTM C303
Corrosion resistance**	Stress Corrosion Cracking Tendency of Austenitic Stainless Steel = Passed Corrosion of Steel = Passed								ASTM C692 ASTM C665
Chemical Analysis**	(Salts: Cl ⁻ , F ⁻ , Na ⁺ , SiO ₄ ⁴⁻) Results fall within acceptability limits of ASTM C795								ASTM C795 / ASTM C871
Thermal Resistance	R-Value / inch @ 75°F RSI value / 25.4mm @ 24°C				4.1 hr. ft ² .°F/BTU 0.72 m ² K/W				ASTM C518 (C177)
Water Absorption/ Vapor Sorption	< 1 % Weight								ASTM C1104
Acoustical Performance		125 Hz	250 Hz	500 Hz	1000 Hz	2000 Hz	4000 Hz	NRC	ASTM C423
	coefficients at 2"	0.28	0.6	1.09	1.09	1.05	1.07	0.95	
	coefficients at 4"	0.86	1.11	1.2	1.07	1.08	1.07	1.1	
Compliance	Complies with Type: IVA								ASTM C612

ROCKWOOL Technical Insulation offers a wide range of facings, dimensions and thicknesses. Please contact us for further information.

** Provisions for lot testing may be required, consult manufacturer.

Surface Burning Characteristics: UL Listed to Canadian standard CAN/ULC S102 ; UL Classified to UL 723



As ROXUL® Inc has no control over installation design and workmanship, accessory materials or application conditions, ROXUL® Inc. does not warranty the performance or results of any installation containing ROXUL® Inc's products. ROXUL® Inc's overall liability and the remedies available are limited by the general terms and conditions of sale. This warranty is in lieu of all other warranties and conditions expressed or implied, including the warranties of merchantability and fitness for a particular purpose.

®/TM: US - owner ROCKWOOL International A/S used under license; Canada - owner Roxul Inc.