

Use: Bonding Polyco PVC Jacket.

Color: White and Clear.

Base: PVC Resin.

Volatile Material: Tetrahydrofuran, cyclohexanone.

% Solids: 15%.

Viscosity: 1200 CPS.

Bonding Time: 20% strength immediately.
80% within 2 hours.
100% within 24 hours.

Shelf Life: 1 year.

Solvents for Clean Up: MEK (Methylethylkeytone).

Service Temperature: -25° to 140°F.

Application Temperature: 40°F - 90°F. Below 40 degrees the adhesive will take longer to dry. Above 90° you have to apply and assemble the parts quickly to keep them from drying out before assembly.

Flash Point: -7° F.

Waybill Notation: Cement N.O.S. (Red Label Required).

Conforms to ASTM D-2564. NSF and USDA Approved

Precautions

Extremely Flammable. Do not use in confined areas as high concentration of vapors may be harmful.



Speedline Corporation

6810 Cochran Road · Solon, OH 44139

Toll Free: 1.800.551.9759 · Tel: 1.800.551.9759 · Fax: 1.440.914.9334

OHIO

6810 Cochran Road
Solon, OH 44139
Tel: 1.800.551.9759

NORTH CAROLINA

501 West Camel Street
Greenboro, NC 27401
Tel: 1.800.551.9760

CALIFORNIA

4113 Gold River Lane
Stockton, CA 95206
Tel: 1.800.833.4500

TEXAS

2902 East 13th St.
Houston, TX 77571
713-670-9700