

SeaRox® SL 620(128)^{NA}

SeaRox SL 620(128)^{NA} is a rigid slab made of stone wool.

Application

SeaRox SL 620(128)^{NA} is primarily used as part of A-class constructions for bulkhead and deck.

Certified according to IMO 2010 FTP Code by DNV-GL.

USCG approved under the Mutual Recognition Agreement (MRA) between US and the EC.



Product properties

Properties	Performance			Norm	
Thermal conductivity	T_m (°F)	25	75	100	ASTM C177
	λ (BTU.in/hr.ft2.°F)	0.22	0.25	0.26	
	T_m (°C)	-4	24	38	
	λ (W/mK)	0.032	0.036	0.037	
Thermal Resistance	R-Value / inch @ 75°F RSI value / 25.4mm @ 24°C	4.0 hr. ft2.°F/BTU 0.70 m² K/W		ASTM C518 (C177)	
Nominal density	8.0 lb/ft3 (128 kg/m³)			EN 1602 / IMO	
Fire classification	Non-combustible Approved for A constructions			IMO 2010 FTP Code	
Water absorption (short term)	< 1 kg/m²			EN 1609	
Max. Application Temperature	Wool: 1382°F (750°C)			-	
Sound absorption directly mounted				ISO 354 (approximated) Evaluated after ISO 11 654	
Facings	-			IMO 2010 FTP Code	



Type approvals	USCG approval number
A60 class steel bulkhead	164.107/EC0575/MEDB00002HN
A60 class steel deck	164.107/EC0575/MEDB00002HT
Non-combustibility	164.109/EC0575/MEDB00001Z8 rev. 4

For more Type approvals please refer to our MED/USCG certificates on rti.rockwool.com

As ROCKWOOL has no control over insulation design and workmanship, accessory materials or applications conditions, ROCKWOOL does not warranty the performance or result of any installation containing ROCKWOOL products. ROCKWOOL's overall liability and the remedies available are limited by the general terms and conditions of sale. This warranty in lieu of all other warranties and conditions expressed or implied, including the warranties of merchantability and fitness for a particular purpose. ROCKWOOL Technical Insulation reserves the right to make necessary product changes at any time. Technical specifications are thus stated subject to change.

ROCKWOOL® Technical Insulation, ROCKWOOL®, SeaRox® and ProRox® are registered trademarks of ROCKWOOL International A/S and cannot be used without a prior written consent.