

# SeaRox® FB 6000 range

The SeaRox FB (Fire Board) 6000 range consists initially of the SeaRox FB 6020, SeaRox FB 6040 and SeaRox FB 6050. This is a unique range of low weight Fire Boards for the marine and offshore market. SeaRox Fire Boards can be supplied with reinforced alu foil on one side.

## Application

SeaRox Fire Boards are used for A-15, A-30 and A-60 class Bulkhead and Deck steel constructions. They are suitable in areas where low weight plays an important role like onboard e.g. passenger ships, naval ships and offshore supply vessels. All solutions for A-15, A-30 and A-60 divisions have been tested and approved according to IMO 2010 FTP code.



## Product properties

Properties	Performance		Norm
Thermal conductivity	T (°C)	10	EN 12667
	$\lambda$ (W/mK)	0,034	
Nominal density	SeaRox FB 6020	40 kg/m <sup>3</sup>	EN 1602 / IMO
	SeaRox FB 6040	60 kg/m <sup>3</sup>	
	SeaRox FB 6050	70 kg/m <sup>3</sup>	
Compressive strength	-		EN 826
Fire classification	Non-combustible Approved for A constructions Low flame-Spread Properties		IMO 2010 FTPC
Water absorption (short term)	< 1 kg/m <sup>2</sup>		EN 1609
Max. application temperature	Facing 80°C		-
Sound absorption directly mounted	SeaRox FB 6020, 70 mm: $\alpha_w = 0.95$ SeaRox FB 6040, 70 mm: $\alpha_w = 0.90$ SeaRox FB 6050, 30 mm: $\alpha_w = 0.55$		ISO 354 (approximated)
Facings (on request)	Reinforced alu foil		IMO 2010 FTPC (low flame - spread)

## Advantages

- Lightest stone wool solutions for A-rated steel divisions
- Excellent thermal and acoustic properties
- Lowest water absorption
- Easy handling and installation
- Tested according to the latest fire test procedure, IMO 2010 FTP Code

## Standard dimensions:

SeaRox FB 6020 - Thickness: 70 mm

SeaRox FB 6040 - Thickness: 35 and 70 mm

SeaRox FB 6050 - Thickness: 30 mm

As ROCKWOOL has no control over insulation design and workmanship, accessory materials or applications conditions, ROCKWOOL does not warranty the performance or result of any installation containing ROCKWOOL products. ROCKWOOL's overall liability and the remedies available are limited by the general terms and conditions of sale. This warranty in lieu of all other warranties and conditions expressed or implied, including the warranties of merchantability and fitness for a particular purpose. ROCKWOOL Technical Insulation reserves the right to make necessary product changes at any time. Technical specifications are thus stated subject to change.

ROCKWOOL® Technical Insulation, ROCKWOOL®, SeaRox® and ProRox® are registered trademarks of ROCKWOOL International A/S and cannot be used without a prior written consent.



0575